

AC



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 639 616 A1

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art.
158(3) EPC

(21) Application number: 94908480.0

(51) Int. Cl.⁶: **C08L 25/00, C08L 51/04,
C08L 71/12**

(22) Date of filing: 02.03.94

(86) International application number:
PCT/JP94/00332

(87) International publication number:
WO 94/20571 (15.09.94 94/21)

(30) Priority: 03.03.93 JP 42586/93

(43) Date of publication of application:
22.02.95 Bulletin 95/08

(64) Designated Contracting States:
DE FR GB IT NL

(71) Applicant: **IDEMITSU KOSAN COMPANY
LIMITED**
1-1, Marunouchi 3-chome
Chiyoda-ku
Tokyo 100 (JP)

(72) Inventor: **OKADA, Akihiko**
216, Imazuasayama
Ichihara-shi,
Chiba-ken 299-01 (JP)
Inventor: **SATO, Noboyuki**
216, Imazuasayama
Ichihara-shi,
Chiba-ken 299-01 (JP)

(74) Representative: **Türk, Dietmar, Dr. rer. nat.**
Türk, Gille, Hrabal, Leifert
Patentanwälte
Brucknerstrasse 20
D-40593 Düsseldorf (DE)

(54) **HIGH-IMPACT POLYSTYRENE RESIN COMPOSITIONS.**

(57) A high-impact polystyrene resin composition comprising a syndiotactic styrene polymer (A) and a polar rubbery elastomer (B), and another high-impact polystyrene resin composition comprising a rubbery elastomer (C) and/or polyphenylene ether (D) in addition to the above composition. These compositions are excellent in thermal resistance, elastic modulus, impact resistance and elongation, thus being utilizable in molding various industrial materials such as electrical and electronics components, industrial structural materials, automotive parts, household electric appliances and, machine parts.

BEST AVAILABLE COPY

EP 0 639 616 A1

TECHNICAL FIELD

The present invention relates to an impact resistant polystyrene composition. More particularly, it pertains to a syndiotactic polystyrene composition which is excellent not only in heat resistance and modulus of elasticity but also in impact resistance and extensibility.

BACKGROUND ART

A styrenic polymer having syndiotactic configuration (hereinafter sometimes abbreviated as SPS) is excellent in heat resistance and chemical resistance but is poor in impact resistance and therefore, it has heretofore been limited in the scope of application usable as a construction material. In order to solve the problem, improvement have been made on the impact resistance of SPS, for example, by blending a rubbery elastomer and/or other thermoplastic resin with SPS. (Refer to Japanese Patent Application Laid-Open Nos. 257950/1987, 146944/1989, 182344/1989, 279944/1989 and 64140/1990.)

For example, there are available SPS containing a styrenic compound as a component and as a rubbery elastomer (refer to Japanese Patent Application Laid-Open No. 146944/1989), a SPS/rubber composition incorporated with a block or graft copolymer containing atactic polystyrene chain as a compatibilizer (refer to Japanese Patent Application Laid-Open No. 279944/1989), and a SPS/rubber composition incorporated with a poly(phenylene ether) (refer to Japanese Patent Application Laid-Open No. 279944/1989) and the like.

However, since there is used in the above-mentioned improved technique, a rubbery component or a block or graft copolymer containing atactic polystyrene chain as a compatibilizer for the purpose of improving the compatibility between SPS and the rubbery component that are incompatible with each other and enhancing the dispersibility and interfacial strength of the rubbery component, the problem still remains unsolved in that the working effect as the compatibilizer and the enhancement of impact resistance have still been insufficient. On the other hand, in the case of adding a large amount of a poly(phenylene ether) for the purpose of enhancing the impact resistance, the addition thereof inevitably brings about the deterioration of the resultant composition with respect to the hue and long-term heat resistance as well as the decrease in the crystallinity of the SPS.

DISCLOSURE OF THE INVENTION

In view of the above, intensive research and investigation were continued by the present inventors in order to solve the above-mentioned problems. As a result, it has been found that such problems can be solved by incorporating a rubbery elastomer having a polar group as a rubber component alone or in combination with another rubbery elastomer into SPS. The present invention has been accomplished on the basis of the aforesaid finding and information.

That is to say, the present invention provides an impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration and 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group; and an impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group and 1 to 100 parts by weight of a (C) rubbery elastomer.

The present invention further provides an impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group and 0.1 to 5 parts by weight of a (D) poly(phenylene ether); and an impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group, 1 to 100 parts by weight of a (C) rubbery elastomer and 0.1 to 5 parts by weight of a (D) poly(phenylene ether).

THE MOST PREFERRED EMBODIMENT TO CARRY OUT THE INVENTION

In the impact resistant polystyrene composition according to the present invention, a styrenic polymer having syndiotactic configuration which constitutes the component (A) is employed as the matrix.

Here, the syndiotactic configuration in the styrenic polymer which has syndiotactic configuration means that its stereochemical structure is of syndiotactic configuration, i.e., the stereostructure in which phenyl groups or substituted phenyl groups as side chains are located alternately at opposite directions relative to

the main chain consisting of carbon-carbon bonds. Tacticity is quantitatively determined by the nuclear magnetic resonance method (^{13}C -NMR method) using carbon isotope. The tacticity as determined by the ^{13}C -NMR method can be indicated in terms of proportions of structural units continuously connected to each other, i.e., a diad in which two structural units are connected to each other, a triad in which three structural units are connected to each other and a pentad in which five structural units are connected to each other. The styrenic polymers having such syndiotactic configuration as mentioned in the present invention usually means polystyrene, poly(alkylstyrene), poly(halogenated styrene), poly(halogenated alkylstyrene), poly(alkoxystyrene), poly(vinyl benzoate), hydrogenated polymer thereof, the mixture thereof, and copolymers containing the above polymers as main components, having such a syndiotacticity as determined by the above-mentioned method that the proportion of racemic diad is at least 75%, preferably at least 85%, or the proportion of racemic pentad is at least 30%, preferably at least 50%. The poly(alkylstyrene) includes poly(methylstyrene), poly(ethylstyrene), poly(isopropylstyrene), poly(tert-butylstyrene), poly(phenylstyrene), poly(vinylnaphthalene) and poly(vinylstyrene). Poly(halogenated styrene) includes poly(chlorostyrene), poly(bromostyrene), and poly(fluorostyrene). Poly(halogenated alkylstyrene) includes poly(chloromethylstyrene). Poly(alkoxystyrene) includes poly(methoxystyrene), and poly(ethoxystyrene).

The particularly desirable styrenic polymers are polystyrene, poly(p-methylstyrene), poly(m-methylstyrene), poly(p-tert-butylstyrene), poly(p-chlorostyrene), poly(m-chlorostyrene), poly(p-fluorostyrene), hydrogenated polystyrene and the copolymer containing the structural units thereof.

The above-mentioned styrenic polymer may be used alone or in combination with at least one other one.

The molecular weight of the styrenic polymer to be used in the present invention is not specifically limited, but is desirably 10,000 or more, more desirably 50,000 or more in terms of weight-average molecular weight. The molecular-weight distribution, that is, the broadening of molecular weight of the styrenic polymer is not specifically limited as well, but may be in a wide range. A weight-average molecular weight of less than 10,000 is unfavorable since the composition or molding obtained therefrom is sometimes deteriorated thereby in the thermal and mechanical properties.

The styrenic polymer having such syndiotactic configuration can be produced by polymerizing a styrenic monomer which corresponds to the above styrenic polymer in the presence or absence of a solvent such as an inert hydrocarbon by the use of a catalyst comprising a titanium compound and a condensation product of water and trialkylaluminum (Japanese Patent Application Laid-Open No. 187708/1987). In addition, the poly(halogenated alkylstyrene) and the hydrogenated product thereof can be produced by the processes described in Japanese Patent Application Laid-Open Nos. 46912/1989 and 178505/1989, respectively.

In the polystyrene composition according to the present invention, there is used a rubbery elastomer having a polar group as the component (B) for the purpose of improving the impact resistance of the composition. A variety of such rubbery elastomers may be employed and exemplified by modified rubbers obtained by modifying with a modifying agent having a polar group, a copolymer rubber of ethylene and a polar vinyl monomer such as polysulfide rubber, thiokol rubber, acrylic rubber, urethane rubber, epichlorohydrin rubber, chlorinated rubber, styrene/butyl-acrylate rubber, ethylene/methyl methacrylate/glycidyl methacrylate copolymer rubber, and ethylene/methyl methacrylate/maleic anhydride copolymer rubber; natural rubber; polybutadiene; polyisoprene; polyisobutylene; neoprene; silicone rubber; styrene/butadiene block copolymer (SBR); a styrene/butadiene/styrene block copolymer (SBS); hydrogenated styrene/butadiene/styrene block copolymer (SEBS); styrene/isoprene block copolymer (SIR); styrene/isoprene/styrene block copolymer (SIS); hydrogenated styrene/isoprene/styrene block copolymer (SEPS); ethylene/propylene rubber (EPM); ethylene/propylene/diene rubber (EPDM); and ethylene/butylene rubber (EBM). Preferable rubbery elastomers having a polar group among these are those obtained by modifying SEBS, SBR, SBS, SEPS and SIS, respectively.

The above-exemplified rubbery elastomer having a polar group may be used alone or in combination with at least one other one.

The polar group is not specifically limited but is exemplified by acid halide, carbonyl group, acid anhydride, acid amide, carbonic acid ester, acid azide, sulfone group, nitrile group, cyano group, isocyanic acid ester group, amino group, hydroxyl group, imide group, thiol group, oxazoline group and epoxy group, of which an acid anhydride is particularly desirable, among which maleic anhydride group and epoxy group are most desirable. The content of the polar group is preferably 0.01% or more by weight based on the rubbery elastomer having a polar group as the component (B).

A content thereof less than 0.01% by weight sometimes makes it impossible to expect the improvement in mechanical strength.

As the component (B) of the present invention, SEBS which has a maleic anhydride group and an epoxy group is preferably employed in particular.

The rubbery elastomer which constitutes the component (C) is used for the purpose same as that of the above-mentioned component (B) and is exemplified by an ethylene/polar vinyl monomer copolymer-rubber such as polysulfide rubber, thiokol rubber, acrylic rubber, urethane rubber, epichlorohydrin rubber, chlorinated rubber, and ethylene/methyl methacrylate/glycidyl methacrylate copolymer rubber; natural rubber; polybutadiene; polyisoprene; polyisobutylene; neoprene; silicone rubber; styrene/butadiene block copolymer (SBR); a styrene/butadiene/styrene block copolymer (SBS); hydrogenated styrene/butadiene/styrene block copolymer (SEBS); styrene/isoprene block copolymer (SIR); styrene/isoprene/styrene block copolymer (SIS); hydrogenated styrene/isoprene/styrene block copolymer (SEPS); ethylene/propylene rubber (EPM); ethylene/propylene/diene rubber (EPDM); and ethylene/butylene rubber (EBM) and a rubber obtained by modifying any of the above-exemplified rubbers. Of these are preferable SEBS, SBR and SBS, among which SEBS is particularly preferable.

The aforesaid rubbery elastomer may be used alone or in combination with at least one other one.

The poly(phenylene ether) as the component (C) is a publicly known compound, and reference may be made to USP Nos. 3306874, 3306875, 3257357 and 3257358.

The poly(phenylene ether) is prepared usually by oxidative coupling reaction forming a homopolymer or a copolymer in the presence of a cupramine complex and at least one di- or tri-substituted phenol. As the cupramine complex there may be used the cupramine complex derived from any of primary, secondary and tertiary amines.

Specific examples of the suitable poly(phenylene ether) include poly(2,3-dimethyl-6-ethyl-1,4-phenylene ether), poly(2-methyl-6-chloromethyl-1,4-phenylene ether), poly(2-methyl-6-hydroxyethyl-1,4-phenylene ether), poly(2-methyl-6-n-butyl-1,4-phenylene ether), poly(2-ethyl-6-isopropyl-1,4-phenylene ether), poly(2-ethyl-6-n-propyl-1,4-phenylene ether), poly(2,3,6-trimethyl-1,4-phenylene ether), poly[2-(4'-methylphenyl)1,4-phenylene ether], poly(2-bromo-6-phenyl-1,4-phenylene ether), poly(2-methyl-6-phenyl-1,4-phenylene ether), poly(2-phenyl-1,4-phenylene ether), poly(2-chloro-1,4-phenylene ether), poly(2-methyl-1,4-phenylene ether), poly(2-chloro-6-ethyl-1,4-phenylene ether), poly(2-chloro-6-bromo-1,4-phenylene ether), poly(2,6-di-n-propyl-1,4-phenylene ether), poly(2-methyl-6-isopropyl-1,4-phenylene ether), poly(2-chloro-6-methyl-1,4-phenylene ether), poly(2-methyl-6-ethyl-1,4-phenylene ether), poly(2,6-dibromo-1,4-phenylene ether), poly(2,6-dichloro-1,4-phenylene ether), poly(2,6-diethyl-1,4-phenylene ether) and poly(2,6-dimethyl-1,4-phenylene ether). Among the above-mentioned poly(phenylene ether), poly(2,6-dimethyl-1,4-phenylene ether) is particularly desirable for use.

The above-mentioned poly(phenylene ether) may be used alone or in combination with at least one other one.

The impact resistant polystyrene composition according to the present invention (hereinafter sometimes abbreviated as "the present composition") comprises the aforesaid components (A) to (D) in combination.

In the case where the present composition is composed of the components (A) and (B), it comprises 100 parts by weight of the component (A) and 1 to 100, preferably 5 to 80 parts by weight of the component (B). An amount of the component (B) less than one (1) part by weight results in insufficient effect on the improvement of the impact resistance, whereas that more than 100 parts by weight brings about remarkable decrease in the modulus of elasticity and heat resistance of the present composition.

In the case where the present composition is composed of the components (A), (B) and (C), it comprises 100 parts by weight of the component (A), 1 to 100, preferably 5 to 80 parts by weight of the component (B) and 1 to 100, preferably 5 to 80 parts by weight of the component (C). In this case, an amount of the component (B) or (C) less than one (1) part by weight results in insufficient effect on the improvement of the impact resistance of the present composition, whereas that more than 100 parts by weight gives rise to remarkable decrease in the modulus of elasticity and heat resistance of the present composition. In addition, the amount of the component (B) is preferably 1 to 50% by weight of the total sum of the components (B) and (C). An amount of the component (B) less than 1% by weight leads to insufficient effect on the improvement of the impact strength and elongation, whereas that more than 50% by weight is unfavorable from the economical point of view. There are preferably used the components (B) and (C) each having the same skeleton or having high compatibility with each other.

In the case where the present composition is composed of the components (A), (B) and (D) or the components (A), (B), (C) and (D), the amount of the component (D) is 0.1 to 5 parts by weight based on 100 parts by weight of the component (A). An amount of the component (D) less than 0.1 part by weight results in insufficient effect on the improvement of the impact resistance of the present composition, while that more than 5 parts by weight leads to poor moldability of the present composition.

The composition according to the present invention may be incorporated as necessary with an additive such as an inorganic filler, a nucleating agent, an antioxidant, a ultraviolet absorber, an external lubricant, a plasticizer, an antistatic agent, a colorant, a flame retardant and a flame retardant aid or another thermoplastic resin insofar as the object of the present invention is not impaired.

As the inorganic filler, mention may be made of various fillers such as fibrous filler, granular filler and powdery filler. Examples of fibrous filler include glass fiber, carbon fiber, whisker, Kevlar fiber, ceramics fiber and metallic fiber. Specific examples of the filler include boron; alumina; silica; and silicon carbide as whisker, gypsum; potassium titanate; magnesium sulfate; and magnesium oxide as ceramics fiber, copper; aluminum; and steel as metallic fiber. The form or shape of the filler includes cloth, mat, bound and cut fiber, short fiber, filament and whisker. The bound and cut fiber has preferably a length of 0.05 to 50 mm and a diameter of 5 to 20 μm . The cloth fiber and mat fiber have preferably a length of at least one (1) mm, particularly at least 5 mm.

Examples of granular or powdery filler include talc, carbon black, graphite, titanium dioxide, silica, mica, calcium carbonate, calcium sulfate, barium carbonate, magnesium carbonate, magnesium sulfate, barium sulfate, oxysulfate, tin oxide, alumina, kaolin, silicon carbide, metallic powder, glass powder, glass flake and glass bead. Among the above-mentioned fillers are preferable in particular the glass fillers such as glass filament, glass fiber, glass roving, glass mat, glass powder, glass flake and glass beads.

The above-mentioned inorganic filler is preferably surface-treated. The purpose of use of the coupling agent to be used for the surface treatment is to improve the adhesivity between the filler and the resin component. The coupling agent may optionally be selected for use from the publicly known silane-based coupling agent and titanium-based coupling agent. Examples of the silane-based coupling agent include triethoxysilane, vinyltris(β -methoxyethoxy)silane, γ -methacryloxypropyl-trimethoxysilane, γ -glycidoxypentyl-trimethoxysilane, β -(1,1-epoxycyclohexyl)ethyl-trimethoxysilane, n - β -(aminoethyl)- γ -aminopropyl-trimethoxysilane, N - β -(aminoethyl)- γ -aminopropyl-methyldimethoxysilane, γ -aminopropyl-triethoxysilane, N -phenyl- γ -aminopropyl-trimethoxysilane, γ -mercaptopropyl-trimethoxysilane, γ -chloropropyl-trimethoxysilane, γ -aminopropyl-trimethoxysilane, γ -aminopropyl-tris(2-methoxyethoxy)silane, N -methyl- γ -aminopropyl-trimethoxysilane, N -vinylbenzyl- γ -aminopropyl-triethoxysilane, triaminopropyl-trimethoxysilane, 3-ureidopropyl-trimethoxysilane, 3-(4,5-dihydroimidazole)propyl-triethoxysilane, hexamethyldisilazane, N,O -(bistrimethylsilyl)amide and N,N -bis(trimethylsilyl)urea. Among them are desirable aminosilane and epoxysilane such as γ -aminopropyl-triethoxysilane, N - β -(aminoethyl)- γ -aminopropyl-triethoxysilane, γ -glycidoxypentyl-trimethoxysilane, β -(3,4-epoxycyclohexyl)ethyl-trimethoxysilane.

Specific examples of the titanium-based coupling agent include isopropyltriisostearoyl titanate, isopropyltridodecylbenzenesulfonyl titanate, isopropyltris(dioctylpyrophosphate)titanate, tetraisopropylbis(dioctylphosphite)titanate, tetraoctylbis(di-tridecylphosphite)titanate, tetra(1,1-diallyloxymethyl-1-butyl)bis(di-tridecyl)phosphite titanate, bis(dioctylpyrophosphate)oxyacetate titanate, bis(dioctylpyrophosphate)ethylene titanate, isopropyltrioctanoyl titanate, isopropyltrimethacrylisostearoyl titanate, isopropylisostearoyldiacrylate titanate, isopropyltri(dioctylphosphate)titanate, isopropyltricumylphenyl titanate, isopropyltri(N -amidoethyl-aminoethyl)titanate, dicumylphenyloxyacetate titanate and di-isostearoyl-ethylene titanate, among which isopropyltri(N -amidoethyl-aminoethyl) titanate is desirable.

The surface treatment of the above-mentioned filler by the use of such coupling agent can be effected by a conventional known method without specific limitation, for example, sizing treatment in which the filler is coated with the sizing agent in the form of solution of the coupling agent as mentioned above in an organic solvent or in the form of suspension containing the coupling agent; dry blending by the use of a Henschel mixer, super mixer, Ready-gel mixer, V-type blender or the like; spraying method; integral blending; dry concentration or the like, each being suitably selected according to the form and shape of the filler to be used. The surface treatment is, however, preferably carried out by means of sizing treatment, dry blending, spraying or the like.

In combination with the aforementioned coupling agent, a film forming substance for glass may be used without specific limitation and is exemplified by the polymer such as polyester-based, urethane-based, epoxy-based, acrylics-based, vinyl acetate-based and isocyanate-based polymers.

Examples of the nucleating agent include a metallic salt of an organic acid and an organic phosphorus compound, of which are preferable an aluminum salt of di- P -tert-butylbenzoic acid, an aluminum salt of p -(tert-butyl)benzoic acid, a sodium salt of cyclohexanecarboxylic acid and a sodium salt of β -naphthoic acid.

Among the organic phosphorus compounds is preferable sodium phosphate of methylenebis(2,4-di-tert-butylphenol) acid.

The nucleating agent may be used alone or in combination with at least one other one.

Examples of the usable antioxidant include (2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphate (produced by Adeka Argus Co., Ltd. under the trademark "PEP-36") and tetrakis[methylene-3-(3',5'-di-tert-

butyl-4'-hydroxyphenyl)]propionate (produced by Adeka Argus Co., Ltd. under the trademark "MARK A060").

The antioxidant may be used alone or in combination with at least one other one.

The present composition is prepared by compounding and blending the aforesaid components (A) and (B) or components (A), (B) and any one of the components (C) and (D) and, as required, another additive and/or another thermoplastic resin.

As a method of blending, there may be optionally adoptable melt kneading method, solution blending method and the like method, each being a conventional known method. As a method of blending the inorganic filler which has been treated with the coupling agent, there may be adoptable, in addition to the aforesaid methods, a method in which a sheet composed of the component (A) or a composition containing the same is laminated with glass mat, followed by melting, a method in which the component (A) or a composition containing the same and a long fiber type inorganic filler are mixed in a liquid to form a slurry, followed by precipitation and heating and the like method. In general, ordinary melt kneading by means of a Banbury mixer, Henschel mixer, kneading roll or the like is preferable.

In the following, the present invention will be described in more detail with reference to preparation examples, examples and comparative examples.

Preparation Example 1

SEBS (produced by Shell Chem. Co. under the trademark "Kraton G-1651") in an amount of 1000 g was dry-blended and melt kneaded along with 30 g of maleic anhydride by the use of a 30 mm twin-screw extruder at a revolution of 200 rpm at a temperature set to 300 °C to produce maleic anhydride-modified SEBS. In order to measure the modification rate of the resultant maleic anhydride-modified SEBS, it was dissolved in chloroform and then reprecipitated in methanol, and the recovered polymer was subjected to Soxhlet extraction using methanol and dried. Thereafter the modification rate was determined from the intensity of carbonyl absorption in infrared (IR) absorption spectrum as well as by titration. As a result, the modification rate of the maleic anhydride-modified SEBS was 0.8% by weight.

Example 1

To 1000 g of SPS (weight-average molecular weight of 360,000, weight-average molecular weight/number-average molecular weight ratio of 2.40) were added 250 g of maleic anhydride-modified SEBS which had been obtained in the Preparation Example 1, 10 g of p-(tert-butyl)aluminum benzoate (produced by Dainippon Ink & Chemicals, Inc. under the trademark "PTBBA-A1) as a nucleating agent, 1 g of (2,6-di-tert-4-methylphenyl)pentaerythritol diphosphite (produced by Adeka Argus Co., Ltd. under the trademark "PEP-36") as an antioxidant and 1 g of tetrakis[methylene-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)]propionate (produced by Adeka Argus Co., Ltd. under the trademark "A060") also as an antioxidant, and the resultant mixture was dry blended with a Henschel mixer. Subsequently, the blend was pelletized with a twin-screw extruder.

The pellet thus obtained was injection molded to produce test pieces for Izod impact test, flexural test and tensile test, respectively. Thus measurements were made of Izod impact strength, extensibility, modulus of elasticity and heat distortion temperature by using the respective test pieces thus obtained. The results obtained are given in Table 1.

Example 2

To 1000 g of SPS (weight-average molecular weight of 360,000, weight-average molecular weight/number-average molecular weight ratio of 2.40) were added 20 g of maleic anhydride-modified SEBS which had a polar group (produced by Asahi Chemical Industry Co., Ltd. under the trademark "M-1913"), 230 g of SEBS (produced by Shell Chem. Co. under the trademark "Kraton G-1651") as a rubbery elastomer, 10 g of p-(tert-butyl)aluminum benzoate (produced by Dainippon Ink & Chemicals, Inc. under the trademark "PTBBA-A1) as a nucleating agent, 1 g of (2,6-di-tert-4-methylphenyl)pentaerythritol diphosphite (produced by Adeka Argus Co., Ltd. under the trademark "PEP-36") as an antioxidant and 1 g of tetrakis-[methylene-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)]propionate (produced by Adeka Argus Co., Ltd. under the trademark "A060") also as an antioxidant, and the resultant mixture was dry blended with a Henschel mixer. Subsequently, the blend was pelletized with a twin-screw extruder.

The pellet thus obtained was injection molded to produce test pieces for Izod impact test, flexural test and tensile test, respectively. Thus measurements were made of Izod impact strength, extensibility,

modulus of elasticity and heat distortion temperature by using the respective test pieces thus obtained. The results obtained are given in Table 1.

Examples 3 to 4

The procedure in Example 2 was repeated to produce test pieces and measure the properties except that the types and the amounts to be used of the rubbery elastomers having a polar group and the rubbery elastomers were altered as shown in Table 1. The results obtained are given in Table 1.

Comparative Examples 1 to 2

The procedure in Example 2 was repeated to produce test pieces and measure the properties except that there were used rubbery elastomers having no polar group as shown in Table 1. The result obtained are given in Table 1.

Table 1

	Component (A)		Component (B)		Component (C)	
	Kind	Parts by weight	Kind	Parts by weight	Kind	Parts by weight
Example 1	SPS	100	Preparation Example 1	25	-	-
Example 2	SPS	100	SEBS* ¹	2	SEBS* ⁴	23
Example 3	SPS	100	SEBS* ²	2	SEBS* ⁴	23
Example 4	SPS	100	EPM* ³	2	EPM* ⁵	23
Comparative Example 1	SPS	100	-	-	SEBS* ⁴	25
Comparative Example 2	SPS	100	-	-	EPM* ⁵	25

Table 1 (continued)

	Izod impact strength* ^A (kJ/m ²)	Elongation* ^B (%)
Example 1	10.8	17.3
Example 2	11.5	20.5
Example 3	10.9	20.0
Example 4	6.8	9.5
Comparative Example 1	5.2	11.1
Comparative Example 2	3.9	6.9

Example 5

To 1000 g of SPS (weight-average molecular weight of 360,000, weight-average molecular weight/number-average molecular weight ratio of 2.40) were added 250 g of maleic anhydride-modified SEBS which had been obtained in the Preparation Example 1, 20 g of poly(2,6-dimethyl-1,4-phenylene

ether), 10 g of p-(tert-butyl)aluminum benzoate (produced by Dainippon Ink & Chemicals, Inc. under the trademark "PTBBA-A1") as a nucleating agent, 1 g of (2,6-di-tert-4-methylphenyl)pentaerythritol diphosphite (produced by Adeka Argus Co., Ltd. under the trademark "PEP-36") as an antioxidant and 1 g of tetrakis-[methylene-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)]propionate (produced by Adeka Argus Co., Ltd. under the trademark "A060") also as an antioxidant, and the resultant mixture was dry blended with a Henschel mixer. Subsequently, the blend was pelletized with a twin-screw extruder.

The pellet thus obtained was injection molded to produce test pieces for Izod impact test, flexural test and tensile test, respectively. Thus measurements were made of Izod impact strength, extensibility, modulus of elasticity and heat distortion temperature by using the respective test pieces thus obtained. The results obtained are given in Table 2.

Example 6

To 1000 g of SPS (weight-average molecular weight of 305,000, weight-average molecular weight/number-average molecular weight ratio of 2.35) were added 20 g of maleic anhydride-modified SEBS which had a polar group (produced by Asahi Chemical Industry Co., Ltd. under the trademark "M-1913"), 230 g of SEBS (produced by Shell Chem. Co. under the trademark "Kraton G-1651") as a rubbery elastomer, 20 g of poly(2,6-dimethyl-1,4-phenylene ether), 10 g of p-(tert-butyl)aluminum benzoate (produced by Dainippon Ink & Chemicals, Inc. under the trademark "PTBBA-A1") as a nucleating agent, 1 g of (2,6-di-tert-4-methylphenyl)pentaerythritol diphosphite (produced by Adeka Argus Co., Ltd. under the trademark "PEP-36") as an antioxidant and 1 g of tetrakis[methylene-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)]propionate (produced by Adeka Argus Co., Ltd. under the trademark "A060") also as an antioxidant, and the resultant mixture was dry blended with a Henschel mixer. Subsequently, the blend was pelletized with a twin-screw extruder.

The pellet thus obtained was injection molded to produce test pieces for Izod impact test, flexural test and tensile test, respectively. Thus measurements were made of Izod impact strength, extensibility, modulus of elasticity and heat distortion temperature by using the respective test pieces thus obtained. The results obtained are given in Table 2.

Examples 7 to 9

The procedure in Example 6 was repeated to produce test pieces and measure the properties except that the types and the amounts to be used of the rubbery elastomers having a polar group and the rubbery elastomers were altered as shown in Table 2. The results obtained are given in Table 2.

Comparative Examples 3 to 5

The procedure in Example 6 was repeated to produce test pieces and measure the properties except that there were used rubbery elastomers having no polar group as shown in Table 2. The result are given in Table 2.

Table 2

	Component (A)		Component (B)		Component (C)	
	Kind	Parts by weight	Kind	Parts by weight	Kind	Parts by weight
Example 5	SPS	100	Preparation Example 1	25	-	-
Example 6	SPS	100	SEBS*1	2	SEBS*4	23
Example 7	SPS	100	SEBS*2	2	SEBS*4	23
Example 8	SPS	100	SEBS*1	2	SEBS*4	23
Example 9	SPS	100	EPM*3	2	EPM*5	23
Comparative Example 3	SPS	100	-	-	SEBS*4	25
Comparative Example 4	SPS	100	-	-	SEBS*4	25
Comparative Example 5	SPS	100	-	-	EPM*5	25

Table 2 (continued)

	Component (D)		Izod impact strength* ^A (kJ/m ²)	*B Elongation (%)
	Kind	Parts by weight		
Example 5	Poly(phenylene ether)*6	2	13.0	19.4
Example 6	Poly(phenylene ether)*6	2	14.0	24.3
Example 7	Poly(phenylene ether)*6	2	13.5	23.8
Example 8	Poly(phenylene ether)*6	4	16.2	29.5
Example 9	Poly(phenylene ether)*6	2	8.5	12.0
Comparative Example 3	Poly(phenylene ether)*6	2	5.9	12.8
Comparative Example 4	Poly(phenylene ether)*6	4	6.4	14.5
Comparative Example 5	Poly(phenylene ether)*6	2	4.2	7.5

Remarks

- *A: According to JIS K 7110 with notch
- *B: According to JIS K 7113
- *1: Maleic anhydride-modified SEBS (M-1913,
produced by Asahi Chemical Industry Co., Ltd.)
- *2: Glycidyl methacrylate-modified SEBS (Z-513,
produced by Asahi Chemical Industry Co., Ltd.)
- *3: Maleic anhydride-modified EPM (T-7711SP,
produced by Japan Synthetic Rubber Co., Ltd.)
- *4: SEBS (Kraton G-1651, produced by Shell Chem.
Co.)
- *5: EPM (EP-07P, produced by Japan Synthetic Rubber
Co., Ltd.)
- *6: Poly(2,6-dimethyl-1,4-phenylene ether)

Industrial Applicability

The impact resistant polystyrene composition according to the present invention is excellent in impact resistance and extensibility and thus is expected to find effective use for molding electric and electronic materials such as connectors and print circuit boards; industrial construction materials; automobile parts such as connectors to be mounted on vehicles, wheel cap, cylinder and head cover; domestic electrical appliances; industrial materials such as various machine parts etc.

Claims

1. An impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration and 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group.
2. An impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group and 1 to 100 parts by weight of a (C) rubbery elastomer.
3. An impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group and 0.1 to 5 parts by weight of a (D) poly(phenylene ether).
4. An impact resistant polystyrene composition which comprises 100 parts by weight of an (A) styrenic polymer having syndiotactic configuration, 1 to 100 parts by weight of a (B) rubbery elastomer having a polar group, 1 to 100 parts by weight of a (C) rubbery elastomer and 0.1 to 5 parts by weight of a (D) poly(phenylene ether).

5. The impact resistant polystyrene composition according to any of Claims 1 to 4 wherein the rubbery elastomer having a polar group as the component (B) is a rubbery elastomer having a maleic anhydride group.
- 5 6. The impact resistant polystyrene composition according to any of Claims 1 to 4 wherein the rubbery elastomer having a polar group as the component (B) is a rubbery elastomer having an epoxy group.
7. The impact resistant polystyrene composition according to any of Claims 1 to 4 wherein the rubbery elastomer having a polar group as the component (B) is a hydrogenated styrene/butadiene/styrene
10 copolymer rubber having an epoxy group.
8. The impact resistant polystyrene composition according to Claim 2 wherein the rubbery elastomer as the component (C) is a hydrogenated styrene/butadiene/styrene copolymer rubber.
- 15 9. The impact resistant polystyrene composition according to Claim 4 wherein the rubbery elastomer as the component (C) is a hydrogenated styrene/butadiene/styrene copolymer rubber.

20

25

30

35

40

45

50

55

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP94/00332

A. CLASSIFICATION OF SUBJECT MATTER

Int. C1⁵ C08L25/00, C08L51/04, C08L71/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int. C1⁵ C08L25/00-25/18, C08L51/00-51/10
C08L71/00-71/14

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho 1926 - 1994

Kokai Jitsuyo Shinan Koho 1971 - 1994

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI/L

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, A, 1-182344 (Idemitsu Kosan Co., Ltd.), July 20, 1989 (20. 07. 89), Claim, line 6, upper left column, line 15, lower right column to line 3, lower left column, page 3 & EP, A1, 318793	1-9
X	JP, A, 1-146944 (Idemitsu Kosan Co., Ltd.), June 8, 1989 (08. 06. 89),	1
A	Claim, lines 5 to 9, lower right column, page 2 & EP, A1, 318793	2-9
A	JP, A, 62-257950 (Idemitsu Kosan Co., Ltd.), November 10, 1987 (10. 11. 87), Claim, (Family: none)	1-9
X	JP, A, 2-64140 (Idemitsu Kosan Co., Ltd.), March 5, 1990 (05. 03. 90), Claim, page 2, lines 3 to 18, upper left column, page 4 & US, A, 5109068 & EP, A1, 356897	3

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reasons (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

May 13, 1994 (13. 05. 94)

Date of mailing of the international search report

June 7, 1994 (07. 06. 94)

Name and mailing address of the ISA/

Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.